

## CALIBER™ XR HEAVY DUTY GREASE

Caliber™ XR is the most robust lithium-based bearing grease in the Whitmore line. This extreme pressure grease was designed for heavy duty service. It is recommended where the most severe high load and shock load are encountered. Applications include steel mill roll stands, slew rings on mining and forestry equipment, and heavily loaded industrial equipment such as mills, grinders, etc.

Whitmore's Caliber™ XR incorporates high fluid viscosity, effective extreme pressure and anti-wear additives, plus solid lubricants. This potent combination ensures long component life and minimal unscheduled stoppages.

By combining a shear-stable lithium thickener with high density polymers, Whitmore has created a grease with outstanding water resistance, whether the application is a shielded bearing or one that is prone to direct water spray.

**BENEFITS:**

- **COMPONENT LIFE** – outstanding wear protection means money saved in component replacement.
- **PUMPABLE** – despite its robust characteristics it can be dispensed below freezing.
- **WATER RESISTANT** – tacky polymers ensure metal adhesion despite direct water spray.
- **SAFE** – contains no hazardous components.

**APPLICATIONS:**

Typical applications for Whitmore's Caliber™ XR include ball and roller bearings, bushings and slides. Caliber™ XR is especially valuable where speeds are low and loads are high. Transportation and material handling equipment applications include king pins, sleeve bearings, u-joints and chassis points.

ASTM #	TYPICAL CHARACTERISTICS			
	NLGI Grade	0	1	2
<b>D-217</b>	<b>Penetration Range</b>	355-385	310-340	265-295
<b>D-2265</b>	<b>Dropping Point, °F (°C)</b>	440 (226)	450 (232)	450 (232)
<b>D-445</b>	<b>Kinematic Viscosity (Base Oil)</b>			
	cSt @ 40°C	1,000	1,000	1,000
	cSt @ 100°C	67	67	67
<b>Gardner Method</b>	<b>Density, lb/gal @ 60°F (15.5°C)</b>	7.5	7.60	7.62
	<b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	.9085	0.9124	0.9131
<b>D-2596</b>	<b>Four Ball EP, Weld Point, kg</b>	620	620	620
<b>D-2266</b>	<b>Four Ball Wear, Scar Width, mm</b>	0.50	0.5	0.50
<b>D-4049</b>	<b>Water Spray Off, % Loss</b>	--	<22	<12
<b>D-1264</b>	<b>Water Washout, % Loss</b>	7	5	4
<b>D-1743</b>	<b>Rust Test</b>	Pass	Pass	Pass
	<b>Thickener Type</b>	Lithium	Lithium	Lithium
<b>OEM Standard</b>	<b>Low Temperature Pumpability</b>			
	Lincoln Ventmeter @ 400 psi, °F (°C)	15 (-10)	18 (-7)	25 (-4)
	Lincoln Ventmeter @ 700 psi, °F (°C)	8 (-13)	10 (-12)	14 (-10)

*The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.*

**PACKAGING**

Drums	Kegs	Pails	Cartridges 50 Per Case
-------	------	-------	---------------------------

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.

