

## DRILL STEEL LUBRICANT

Whitmore's Drill Steel Lubricant is an anti-seize composition for use on rock drill tool joints, drill stems and couplings. Drill Steel Lubricant is specifically formulated to contain no heavy metals (lead-free).

It contains superior friction-reducing additives which minimize "make-up" and "break-out" torque, while virtually eliminating thread wear. In addition, Drill Steel Lubricant protects metal parts from rust and corrosion, even in the most adverse atmospheres. The unique metallic, film-forming characteristics of Drill Steel Lubricant provide a protective shield against shock load and thread seizure.

Drill Steel Lubricant protects against high temperatures and eliminates run-out, even under severe operating conditions. By eliminating metal-to-metal contact, Drill Steel Lubricant extends the useful life of drill steel and reduces labor required for assembly and disassembly.

### BENEFITS:

- LEAD-FREE - contains no heavy metals.
- SUPERIOR FRICTION REDUCING ADDITIVE PACKAGE - minimizes "make-up" and "break-out" torque.
- EXTENDS EQUIPMENT LIFE - eliminates metal-to-metal contact.

### APPLICATIONS:

Drill Steel Lubricant is recommended for all types of rotary drilling joints: API buttress threads, square threads, high lead thread and special shouldered joints. Additionally, this product can be used on studs, bolts, fittings, pipe threads, gaskets, flanges, seals, packings, sliding surfaces and press fittings. It is an excellent lubricant for use on tappings, lathe centers, highly loaded surfaces, ways, tracks, tubular joints of all sizes and types, valve stems, tapes, sleeves, screws, drills and drawing and forming equipment.

ASTM #		TYPICAL CHARACTERISTICS	
		Drill Steel Lubricant Winter	Drill Steel Lubricant
D-217	Cone Penetration (Worked)	290-320	215-265
D-2265	Dropping Point, °F (°C)	>430 (>221)	>500 (>260)
Gardner Method	Density, lb/gal @ 60°F (15.5°C)	9.9	9.9
	Specific Gravity, g/cc @ 60°F (15.5°C)	1.19	1.19
D-2596	Four Ball EP		
	Weld Point, kg	800	620
	Load Wear Index	129	92
D-4049	Water Spray-Off, % Loss	<10	<10
D-4048 (Modified)	Copper Strip Corrosion for Greases 212°F (100°C) @ 3 hrs	1A	1A
	Thickener Type	Aluminum Complex	Aluminum Complex

*The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.*

### PACKAGING

Drums	Pails	Caulking Tubes 12 per case	Caulking Tubes 24 per case
-------	-------	-------------------------------	-------------------------------

For warranty information, scan the QR code.  
 You can also email us at [sales@whitmores.com](mailto:sales@whitmores.com)  
 Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
 An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

