

## NOVATEMP™ HIGH TEMP LUBRICANT

Novatemp™ is designed to lubricate bushings and other sliding components at high temperatures.

At high temperatures the solids in Novatemp™ take over as the fluid carrier portion evaporates. Novatemp™ contains almost 15% lubricating solids. Long after the base oil has evaporated due to heat, the MoS<sub>2</sub> and graphite provide a laminating film that protects sliding machine elements. Novatemp™ loses its "greasiness" and becomes a dry film lubricant.

Novatemp™ provides this extra measure of lubrication without the use of lead.

Although it has the appearance of a normal bearing grease, Novatemp™ is not ideal for use on precision roller or ball bearings with internal clearance C2 or CN. The high proportion of solid lubricants can be a detriment for precision bearings. For these anti-friction bearings, use Whitmore's Matrix® high performance grease.

### BENEFITS:

- HIGH TEMPERATURE PERFORMANCE - fluid carrier dissipates at elevated temperatures, depositing a protective film of solid lubricants on moving parts. It protects at temperatures up to 1200°F (650°C) in the dry lubricant phase.
- ALUMINUM COMPLEX SOAP THICKENER - may be used to lubricate sliding component at normal ambient, as well as high temperatures.
- SOLID FILM LUBRICANTS - MoS<sub>2</sub> and graphite plate out on metal surfaces, reducing metal-to-metal contact and wear.

### APPLICATIONS:

Novatemp™ is recommended for the lubrication of bearings and bushings that operate at temperatures up to 1200°F (650°C). Typical applications include kiln car wheel bearings, oven door hinges, threaded fittings, oven conveyors and furnace bearings. Use only in bearings designed for high temperature application, with internal clearance C3 or greater.

ASTM #		TYPICAL CHARACTERISTICS
	<b>Grade</b>	1.5
D-217	<b>Cone Penetration (Worked)</b>	290-320
D-2265	<b>Dropping Point, °F (°C)</b>	>550 (>260)
D-445	<b>Kinematic Viscosity (Base Oil)</b> cSt @ 40°C cSt @ 100°C	490 32
D-2161	<b>Saybolt Viscosity (Base Oil)</b> SUS @ 100°F SUS @ 210°F	2,600 156
<b>Gardner Method</b>	<b>Density, lb/gal @ 60°F (15.5°C)</b> <b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	7.50 0.901
D-2266	<b>Four Ball Wear</b> Scar Width, mm	0.70
D-1743	<b>Rust Test</b>	Pass
D-4048 (Modified)	<b>Copper Strip Corrosion for Greases</b> 212°F (100°C) @ 3 hrs	1B
	<b>Thickener Type</b>	Aluminum Complex
<b>OEM Standard</b>	<b>Low Temperature Pumpability</b> Lincoln Ventmeter @ 400 psi, °F (°C)	10 (-12)
D-92	<b>Flash Point, °F (°C)</b> Cleveland Open Cup (Base Oil)	>580 (>304)
	<b>Solid Lubricants</b>	MoS <sub>2</sub> /Graphite

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

### PACKAGING

Drums	Kegs	Pails	Cartridges 50 per case
-------	------	-------	---------------------------

For warranty information, scan the QR code.  
You can also email us at [sales@whitmores.com](mailto:sales@whitmores.com)  
Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

