

## OMNILITH™ 500 EXTREME PRESSURE GREASE

Omnilith™ 500 is an extreme pressure grease suitable for use in severe applications across a wide variety of operating conditions including high load, moisture, and a wide speed range.

The lithium complex soap base allows for use at temperatures up to 450°F (232°C). Omnilith™ 500 EP 2 is the ideal choice as multipurpose grease in heavy-duty industry where extreme pressure or high temperature performance is required.

Omnilith™ 500 EP 1 grade is softer and is highly recommended for use in auto-lube systems and in winter conditions.

Maximum DN factor: 300,000 (NLGI Grade 2)  
 Maximum continuous temperature: 350°F (177°C)  
 Maximum occasional temperature: 450°F (232°C)  
 Appearance: Red, Tacky

### BENEFITS:

- RESISTS WEAR - extends equipment life.
- WATER RESISTANT - stays in place when exposed to moisture.
- CORROSION INHIBITED - protects metal parts from effects of oxidation.
- MECHANICALLY STABLE - resists separation. Excellent for pumping through automatic lubrication systems.

### APPLICATIONS:

Universal grease for multiple applications, i.e. moisture, dust, vibration, shock loads, and extreme pressure. Suitable for use on electric motors, construction machines, vehicle wheel bearings and chassis points, agricultural equipment, cranes, stackers, conveyor trolley bearings, and general industrial equipment. In wet or dirty environments, i.e. service stations, textile washing machines, pumps. In heavily loaded antifriction and plain bearings of mobile equipment, i.e. tie rod joints, universal joints, brake camshafts and splined shafts of motor vehicles, threaded spindles and guides of hoists, and bearing surfaces exposed to heavy loads.

ASTM #	Grade	TYPICAL CHARACTERISTICS	
		1	2
D-217	Cone Penetration (Worked)	310-340	265-295
D-566	Dropping Point, °F (°C)	500 (260)	500 (260)
D-445	Kinematic Viscosity (Base Oil with Polymer) cSt @ 40°C cSt @ 100°C	455	455
		31	31
D-445	Kinematic Viscosity (Base Oil) cSt @ 40°C cSt @ 100°C	278	278
		22.5	22.5
Gardner Method	Density, lb/gl @ 60°F (15.5°C)	7.60	7.65
	Specific Gravity, g/cc @ 60°F (15.5°C)	0.913	0.919
D-2596	Four Ball EP, Weld Point, kg	800	800
D-2266	Four Ball Wear, Scar Width, mm	0.56	0.56
D-1264	Water Washout, % Loss	<10	<5
D-1743	Rust Test	Pass	Pass
D-4048 Modified	Copper Strip Corrosion for Greases 212°F (100°C) @ 3 hrs	1B	1B
	Thickener Type	Lithium Complex	Lithium Complex
	Color	Red	Red
OEM Standard	Low Temperature Pumpability Lincoln Ventmeter @ 400 psi, °F (°C)	0 (-18)	10 (-12)
	Ambient temperature range, °F (°C)	-13 (-25) to 300 (150)	0 (-18) to 300 (150)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

### PACKAGING

Shuttle Tanks	Drums	Kegs	Pails	Cartridges 50 per case
---------------	-------	------	-------	---------------------------

For warranty information, scan the QR code.  
 You can also email us at [sales@whitmores.com](mailto:sales@whitmores.com)  
 Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
 An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

